



INFORMATION BULLETIN

Epic® 70 LD

DESCRIPTION: Low-density alumina brick with good insulation value while providing high refractoriness.

USES INCLUDE: Insulation in extreme high-temperature applications, as well as those where the insulator may occasionally come into contact with slag and/or metal.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al ₂ O ₃	77.0%
SiO ₂	21.0%
Fe ₂ O ₃	0.4%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	30
Bulk Density pcf (g/cm ³):	84 (1.35)
Cold Crushing Strength psi (MPa):	870 (6)
Linear Change (%):	0.4
8 hrs @ temp ° C (° F):	1730 (3146)
Refractoriness Under Load:	
° C (° F)	1500 (2732)
Thermal Conductivity BTU/SF/hr ² (W/mk):	
@ 400° C (752° F)	0.79 (5.48)
@ 800° C (1472° F)	0.90 (6.24)
@ 1000° C (1832° F)	1.03 (7.14)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
